

739 95 Bystřice 1260
Czech Republic

tel.: +420 558 340 011, 588 340 034

fax.: +420 558 340 100

[e-mail: info@jap.cz](mailto:info@jap.cz)

www.jap.cz

IČO: 48398233 VAT: CZ48398233



Application:

- Rough carburizing during steel melting.
- Soft carburizing in secondary metallurgy.
- Slag foaming during steel melting in electric arc furnaces.
- As a supplement in moulding mixtures.

For above mentioned purposes we offer the materials as follows:

calcined petrol coke

graphite carburizer

Physical Chemical properties:

Calcined petrol coke

Content of carbon	%	min. 98
Content of sulphur	%	max. 0,8
Content of ash	%	max. 0,8
Volatile matter	%	max. 0,5
Moisture	%	max. 0,5

Graphite carburizer

Content of carbon	%	min. 98
Content of sulphur	%	max. 0,1
Content of ash	%	max. 0,8
Volatile matter	%	max. 0,8
Moisture	%	max. 0,5

Packing:

Big bag or smaller bags according to the client's requirement.